



CSP™-TPO *

COMMERCIAL ROOFING

CSP™-TPO 60 | 60 mils

Base Fabric	Standard	Metric
Base Fabric Weight	3.01 oz / yd ²	102 g / m ²
Fiber/Style	Polyester - Aramid / Knit	

Coated Fabric	Standard	Metric
Thickness, overall	60 (+/- 6) mils	1.52 (+/- 0.01) mm
Thickness, over scrim (min)	15 mils	0.38 mm
Coating Type	TPO	

Material Properties	ASTM Test Methods	Standard	Metric
Tensile Strength, Grab (Warp / Fill)	D751A	275 / 300 lbs	1,220 / 1,330 N
Tear Strength, 6.5" x 7" specimen (Warp / Fill)	D751B (mod)	65 / 65 lbs	289 / 289 N
Properties After Oven Aging (retained) Tensile Strength, Grab Tensile Elongation Tear Strength Weight Change	D573		90% 90% 60% +/- 1%
Puncture Strength (FTMS 101C)	Method 2031	275 lbs	1,220 N
Hydrostatic Resistance	D751A	450 psi	3.1 MPa
Seam Adhesion (thermal)	D751	35 lbs / in	61 N / cm
Abrasion Resistance (H18 / 1 kg)	D3884	2,000 cycles	
Ozone Resistance (no cracks)	D1149	Pass	
Water Absorption	D471	< 1 %	
Dimensional Stability (1 hr / 100°C)	D1204	< 1 %	
Solar Reflectance (white)	C1549	0.79	
Solar Emittance (white)	E408	0.87	
Solar Reflective Index	E1980	98	
Low Temp	D2136	-40°F	-40°C
High Temp, Cont/Interm.	D1204	180 / 200°F	82 / 93°C

* in cooperation with **Cooley/Building Products**

The information contained herein or that is supplied by us, or on our behalf, is based upon data obtained through our own research and is considered accurate. However, no warranty is expressed or implied regarding the accuracy of this data, the results obtained from the use thereof, or that any such use will not infringe upon any patent. This information is furnished upon the condition that the person receiving it shall evaluate its suitability for the specific application.

